

Citation 2

HEAT-RESISTANT LACTIC ACID POLYMER MOLDING

Patent number: JP8193165 (Japanese Patent Appln. Opened No. 193165/96)
Publication date: 1996-07-30
Inventor: SUZUKI KAZUHIKO; NAKADA TOMOYUKI;
WATANABE TAKAYUKI; KITAHARA YASUHIRO;
AJIOKA MASANOBU
Applicant: MITSUI TOATSU CHEMICALS
Classification:
- international: C08L67/04; B29C43/02; B29C49/00; C08K3/36;
C08K5/103; B29C45/00; C08L67/04; C08L9/06;
B29K67/00
- european: B29C43/00B
Application number: JP19940313009 19941216
Priority number(s): JP19940280810 19941115; JP19940313009 19941216;
JP19930327858 19931224

Report a data error here

Abstract of JP8193165

PURPOSE: To obtain a lactic acid polymer molding which decomposes in the natural environment and has improved heat resistance and impact strength by mixing a lactic acid polymer, poly-ε-caprolactone, and a specific inorg. crystalline powder, melting the mixture, charging the melt into a metal mold, and molding it while simultaneously crystallizing it. CONSTITUTION: 75-95wt.% lactic acid polymer and 5-25wt.% poly-ε-caprolactone having a wt. average mol.wt. of 50,000-250,000 are mixed in such a manner that the resulting compsn. has an L-lactic acid ratio of 75wt.% or higher. 100 pts.wt. compsn. thus obt'd., 0.1-15 pts.wt. inorg. crystalline powder having an SiO₂ content of 50wt.% or higher and a pH of 8.5 or lower, and, if necessary, 1-20 pts.wt. polyester formed from an aliph. polyhydric alcohol and an aliph. polybasic acid or from an aliph. polyhydric alcohol, an aliph. polybasic acid, and a hydroxycarboxylic acid are mixed, melted, charged into a metal mold kept at 85-125 deg.C of a molding machine, and molded and simultaneously crystallized, giving a heat-resistant lactic acid polymer molding resistant to a temp. of 100-160 deg.C.

Data supplied from the esp@cenet database - Worldwide